

WHAT IS CLAIMED IS:

1. An ultrafine copper alloy wire with a diameter of not more than 0.08 mm,

5 said ultrafine copper alloy wire being formed of a copper alloy wire comprising high-purity copper having a total unavoidable impurity content of not more than 1 ppm by mass and, added to the high-purity copper, 1.0 to 5.0% by mass of silver having a purity of not less than 99.99% by mass.

10 2. An ultrafine copper alloy wire with a diameter of not more than 0.08 mm,

 said ultrafine copper alloy wire being formed of a copper alloy wire comprising high-purity copper having a total unavoidable impurity content of not more than 1 ppm by mass and,
15 added to the high-purity copper, 1.0 to 5.0% by mass of silver having a purity of not less than 99.99% by mass and 0.01 to 0.5% by mass of magnesium having a purity of not less than 99.9% by mass.

 3. An ultrafine copper alloy wire with a diameter of not
20 more than 0.08 mm,

 said ultrafine copper alloy wire being formed of a copper alloy wire comprising high-purity copper having a total unavoidable impurity content of not more than 1 ppm by mass and, added to the high-purity copper, 1.0 to 5.0% by mass of silver
25 having a purity of not less than 99.99% by mass and 0.01 to 0.3% by mass of indium having a purity of not less than 99.99% by mass.

 4. The ultrafine copper alloy wire according to claim 1,

2, or 3, wherein said copper alloy wire has thereon a tin plating, a silver plating, a nickel plating, a tin-lead solder plating, a tin-silver plating, a tin-copper plating, a tin-silver-copper plating, or a tin-silver-copper-bismuth plating.

5 5. A stranded copper alloy wire conductor comprising a plurality of copper alloy wires with a diameter of not more than 0.08 mm stranded together,

 said copper alloy wire comprising high-purity copper having a total unavoidable impurity content of not more than 1
10 ppm by mass and, added to the high-purity copper, 1.0 to 5.0% by mass of silver having a purity of not less than 99.99% by mass.

 6. A stranded copper alloy wire conductor comprising a plurality of copper alloy wires with a diameter of not more
15 than 0.08 mm stranded together,

 said copper alloy wire comprising high-purity copper having a total unavoidable impurity content of not more than 1 ppm by mass and, added to the high-purity copper, 1.0 to 5.0% by mass of silver having a purity of not less than 99.99% by
20 mass and 0.01 to 0.5% by mass of magnesium having a purity of not less than 99.9% by mass.

 7. A stranded copper alloy wire conductor comprising a plurality of copper alloy wires with a diameter of not more than 0.08 mm stranded together,

25 said copper alloy wire comprising high-purity copper having a total unavoidable impurity content of not more than 1 ppm by mass and, added to the high-purity copper, 1.0 to 5.0% by mass of silver having a purity of not less than 99.99% by

mass and 0.01 to 0.3% by mass of indium having a purity of not less than 99.99% by mass.

8. An extrafine coaxial cable comprising a copper alloy wire with a diameter of not more than 0.08 mm provided for
5 constituting an inner conductor or an outer conductor,

said copper alloy wire comprising high-purity copper having a total unavoidable impurity content of not more than 1 ppm by mass and, added to the high-purity copper, 1.0 to 5.0% by mass of silver having a purity of not less than 99.99% by
10 mass.

9. An extrafine coaxial cable comprising a copper alloy wire with a diameter of not more than 0.08 mm provided for constituting an inner conductor or an outer conductor,

said copper alloy wire comprising high-purity copper
15 having a total unavoidable impurity content of not more than 1 ppm by mass and, added to the high-purity copper, 1.0 to 5.0% by mass of silver having a purity of not less than 99.99% by mass and 0.01 to 0.5% by mass of magnesium having a purity of not less than 99.9% by mass.

20 10. An extrafine coaxial cable comprising a copper alloy wire with a diameter of not more than 0.08 mm provided for constituting an inner conductor or an outer conductor,

said copper alloy wire comprising high-purity copper having a total unavoidable impurity content of not more than 1
25 ppm by mass and, added to the high-purity copper, 1.0 to 5.0% by mass of silver having a purity of not less than 99.99% by mass and 0.01 to 0.3% by mass of indium having a purity of not less than 99.99% by mass.

11. The extrafine coaxial cable according to claim 8, 9 or 10, wherein the inner conductor comprises a plurality of the copper alloy wires stranded together.

12. A process for producing an ultrafine copper alloy
5 wire, comprising the steps of:

melting a high-purity copper having a total unavoidable impurity content of not more than 1 ppm by mass in a carbon crucible installed in a vacuum;

replacing an atmosphere surrounding the melted copper by
10 an argon gas atmosphere and adding 1.0 to 5.0% by mass of silver having a purity of not less than 99.99% by mass to said copper;

casting said copper with silver added thereto in a carbon mold into a wire rod; and

15 drawing said wire rod to a diameter of not more than 0.08 mm.

13. A process for producing an ultrafine copper alloy wire, comprising the steps of:

melting a high-purity copper having a total unavoidable
20 impurity content of not more than 1 ppm by mass in a carbon crucible installed in a vacuum;

replacing an atmosphere surrounding the melted copper by an argon gas atmosphere and adding, to said copper, 1.0 to 5.0% by mass of silver having a purity of not less than 99.99% by
25 mass and 0.01 to 0.5% by mass of magnesium having a purity of not less than 99.9% by mass;

casting said copper with silver and magnesium added thereto in a carbon mold into a wire rod; and

drawing said wire rod to a diameter of not more than 0.08 mm.

14. A process for producing an ultrafine copper alloy wire, comprising the steps of:

5 melting a high-purity copper having a total unavoidable impurity content of not more than 1 ppm by mass in a carbon crucible installed in a vacuum;

 replacing an atmosphere surrounding the melted copper by an argon gas atmosphere and adding, to said copper, 1.0 to 5.0%
10 by mass of silver having a purity of not less than 99.99% by mass and 0.01 to 0.3% by mass of indium having a purity of not less than 99.99% by mass;

 casting said copper with silver and indium added thereto in a carbon mold into a wire rod; and

15 drawing said wire rod to a diameter of not more than 0.08 mm.